# LUMINANCE 6901 COLOUR CHART

| | | boxes of 76 | boxes of 38 | boxes of 16 | pigments | Lightfastness |
|---|---|---|---|---|---|---|
| 001 | White | ● | ● | ● | PW6 | LFI |
| 002 | Silver grey | ● | ● | | PB15/PBk6 | LFI |
| 004 | Steel grey | ● | | | PB15/PBk6 | LFI |
| 009 | Black | ● | ● | ● | PBk6 | LFI |
| 015 | Olive yellow | ● | ● | | PBk6/PY3 | LFI |
| 025 | Green ochre | ● | ● | | PY3/PY42/PY13/PO62/PBk6 | LFII |
| 030 | Orange | ● | ● | ● | PO62 | LFI |
| 034 | Yellow Ochre | ● | ● | ● | PY42/PY3 | LFI |
| 036 | Raw sienna | ● | | | PY42 | LFI |
| 037 | Brown ochre | ● | ● | | PY42/PR101/PBk9 | LFI |
| 039 | Olive Brown | ● | | | PY42/PBk9 | LFII |
| 041 | Apricot | ● | | | PO61 | LFII |
| 046 | Cassel earth | ● | ● | | PR101/PBr7/PBk6/PBk11 | LFI |
| 061 | Permanent red | ● | ● | ● | PR242 | LFI |
| 065 | Russet | ● | ● | ● | PR101/PR188/PY42 | LFI |
| 069 | Burnt sienna | ● | ● | ● | PR101/PBk6 | LFI |
| 070 | Scarlet | ● | | | PR254 | LFII |
| 077 | Burnt ochre | ● | ● | | PY42/PR101 | LFI |
| 083 | Ultramarine pink | ● | | | PR259 | LFII |
| 093 | Violet grey | ● | | | PR101/PY42/PV23/PBk6/PBk11 | 1LFI |
| 095 | Light aubergine | ● | | | PR101/PV23/PBk6 | LFI |
| 112 | Manganese violet | ● | ● | ● | PV16 | LFI |
| 120 | Violet | ● | ● | | PV23 | LFII |
| 129 | Violet brown | ● | ● | | PR101/PV23/PY42/PBk9 | LFII |
| 159 | Prussian blue | ● | ● | | PB27 | LFI |
| 161 | Light blue | ● | | | PB15:3/PBk9 | LFII |
| 162 | Phthalocyanine blue | ● | ● | ● | PB15:3 | LFI |
| 171 | Turquoise blue | ● | ● | | PB15:3/PG7/PBk9 | LFII |
| 180 | Malachite green | ● | ● | | PG7/PBk9 | LFI |
| 181 | Light malachite green | ● | | | PG7/PBk9 | LFI |
| 182 | Cobalt green | ● | | | PG50 | LFI |
| 185 | Ice blue | ● | | | PB16 | LFI |
| 214 | Beryl green | ● | | | PG7 | LFI |
| 220 | Grass green | ● | ● | | PY1/PY3/PG7 | LFI |
| 225 | Moss green | ● | ● | | PY3/PB60/PBk6 | LFI |
| 240 | Lemon yellow | ● | ● | ● | PY3 | LFI |
| 242 | Primerose | ● | | | PY42/PY195 | LFI |
| 350 | Purplish red | ● | ● | | PR122/PR179 | LFII |

| | | boxes of 76 | boxes of 38 | boxes of 16 | pigments | Lightfastness |
|---|---|---|---|---|---|---|
| 407 | Sepia | ● | | | PR101/PBr7/PBk6/PBk11 | LFI |
| 470 | Spring green | ● | ● | ● | PY3/PG7 | LFI |
| 495 | Slate greyGraphite | ● | ● | ● | Graphite | LFI |
| 504 | Payne's grey 30% | ● | | | PB29/PBk6 | LFI |
| 507 | Payne's grey 60% | ● | | | PB29/PBk6 | LFII |
| 508 | Payne's grey | ● | ● | | PB29/PBk6 | LFI |
| 548 | Raw umber | ● | ● | ● | PR101/PY42/PBk11 | LFI |
| 571 | Anthraquinoid pink | ● | ● | | PR168 | LFI |
| 585 | Perylene brown | ● | ● | ● | PR179 | LFI |
| 589 | Crimson alizarin (hue) | ● | | | PR178/PV19 | LFII |
| 599 | Crimson aubergine | ● | | | PR179/PV19/PB15 | LFI |
| 630 | Ultramarine violet | ● | | | PV15 | LFI |
| 660 | Middle cobalt blue (hue) | ● | | | PB15/PB29 | LFII |
| 661 | Light cobalt blue | ● | ● | ● | PB28 | LFI |
| 662 | Genuine cobalt blue | ● | | | PB28 | LFI |
| 729 | Dark English green | ● | | | PG7/PBk9 | LFI |
| 732 | Olive brown 10% | ● | | | PY42/PBk9 | LFI |
| 736 | Olive brown 50% | ● | | | PY42/PBk9 | LFI |
| 739 | Dark sap green | ● | ● | ● | PG7/PBk6 | LFI |
| 755 | Grey blue | ● | | | PB15/PB27/PBk6 | LFI |
| 801 | Buff titanium | ● | | | PY151/PR101 | LFII |
| 802 | French grey 10% | ● | | | PY42/PR101/PBk6 | LFI |
| 803 | French grey 30% | ● | | | PY42/PR101/PBk6 | LFI |
| 808 | French grey | ● | ● | | PY42/PR101/PBk6 | LFI |
| 810 | Bismuth yellow | ● | | | PY184 | LFI |
| 820 | Golden Bismuthyellow | ● | ● | | PY184 | LFI |
| 821 | Naples ochre | ● | ● | | PY42/PY184/PBr7 | LFI |
| 832 | Brown ochre 10% | ● | | | PR101/PY42/PBk9 | LFI |
| 836 | Brown ochre 50% | ● | | | PR101/PY42/PBk9 | LFII |
| 842 | Raw umber 10% | ● | | | PR101/PY42/PBk11 | LFI |
| 846 | Raw umber 50% | ● | | | PR101/PY42/PBk11 | LFI |
| 850 | Cornelian | ● | ● | | PO61 | LFI |
| 862 | Burnt sienna 10% | ● | ● | | PR101/PBk6 | LFI |
| 866 | Burnt sienna 50% | ● | | | PR101/PBk6 | LFI |
| 872 | Burnt ochre 10% | ● | ● | | PR101/PY42 | LFI |
| 876 | Burnt ochre 50% | ● | | | PR101/PY42 | LFI |
| 902 | Sepia 10% | ● | | | PR101/PBr7/PBk6/PBk11 | LFI |
| 906 | Sepia 50% | ● | | | PR101/PBr7/PBk6/PBk11 | LFI |